BIC GRAPHIC
14421 MYERLAKE CIRCLE
CLEARWATER PINELLAS
FL 33760 UNITED STATES

The following samples were submitted and identified on behalf of the client as:

SCOTT FLANNEL FLEECE BLANKET

SGS Case No.	:	CA319202530829
Item No.	:	26176
Test Request Form No.	:	3250_HK
Quantity Submitted	:	24 PCS OF 4 STYLES
Manufacturer Date	:	2018
Shipment Order No.	:	7078575
Country of Origin	:	CHINA
Country of Destination	:	CANADA, UNITED STATES
Sample Receiving Date	:	JUN 19, 2019
Test Performing Date	:	JUN 19 - 28, 2019

Test Requested : Please refer to the result summary.

Test Method & Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
1. US California Proposition 65 (County of Marin Case No. CIV 1104003) – Lead content	PASS
2. Flammability of Blankets (ASTM D4151- 10)	--

Signed for and on behalf of
SGS Hong Kong Ltd.

Che Wai Leuk, Jerry
Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Test Results :

1. US California Proposition 65 –Lead Content

Method (non-metallic materials): With reference to CPSC-CH-E1002-08.3 - Standard Operation Procedure for Determining Total Lead (Pb) in Non-Metal Children Product

Test Item(s)	**Lead (Pb)**
Specimen Description	**Result(s) (ppm)**
1. Black fabric (Main fabric) (#1-26176 black mink main fabric)	ND
2. Navy fabric (Main fabric) (#3-26176 navy mink main fabric)	ND
3. Red fabric (Main fabric) (#4-26176 red mink main fabric)	ND
4. Royal fabric (Main fabric) (#5-26176 royal mink main fabric)	ND

Note:
- ppm = parts per million
- ND = Not Detected (lower than MDL)
- MDL = Method Detection Limit =10 ppm
- 1% = 10000mg/kg=10000ppm

Remark: 1. Material information of the sample is provided by the client.
2.Summary of reference limit(s) of Lead requirement:

Requirement(s)		**Reference Limit of Lead (ppm)**
California Proposition 65 (County of Marin Case No. CIV 1104003)	Paint and surface coating	90
	All other materials	100

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

2. Flammability of Blankets (ASTM D4151- 10)

Sample: A

Test results

	Specimen	Burning, charring, and discoloration of paper monitor
Face	1	No
	2	No
	3	No
	4	No
	5	No
Back	1	No
	2	No
	3	No
	4	No
	5	No

Remark
Gas used: Methane
Flame application time: 1 second

Comment
The submitted sample complies with the Class I requirement.

Note
Class I: If none of the paper monitors burn, char, or become discolored after exposing the specimens to the ignition source, the material is classified as Class I.

Class I textiles are generally considered by the trade as having no unusual burning characteristics and acceptable for use in manufacturing blankets.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Flammability of Blankets (ASTM D4151- 10)

Sample: B

Test results

	Specimen	Burning, charring, and discoloration of paper monitor
Face	1	No
	2	No
	3	No
	4	No
	5	No
Back	1	No
	2	No
	3	No
	4	No
	5	No

Remark
Gas used: Methane
Flame application time: 1 second

Comment
The submitted sample complies with the Class I requirement.

Note
Class I: If none of the paper monitors burn, char, or become discolored after exposing the specimens to the ignition source, the material is classified as Class I.

Class I textiles are generally considered by the trade as having no unusual burning characteristics and acceptable for use in manufacturing blankets.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Flammability of Blankets (ASTM D4151- 10)

Sample: C

Test results

	Specimen	Burning, charring, and discoloration of paper monitor
Face	1	No
	2	No
	3	No
	4	No
	5	No
Back	1	No
	2	No
	3	No
	4	No
	5	No

Remark
Gas used: Methane
Flame application time: 1 second

Comment
The submitted sample complies with the Class I requirement.

Note
Class I: If none of the paper monitors burn, char, or become discolored after exposing the specimens to the ignition source, the material is classified as Class I.

Class I textiles are generally considered by the trade as having no unusual burning characteristics and acceptable for use in manufacturing blankets.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Flammability of Blankets (ASTM D4151- 10)

Sample: D

Test results

	Specimen	Burning, charring, and discoloration of paper monitor
Face	1	No
	2	No
	3	No
	4	No
	5	No
Back	1	No
	2	No
	3	No
	4	No
	5	No

Remark
Gas used: Methane
Flame application time: 1 second

Comment
The submitted sample complies with the Class I requirement.

Note
Class I: If none of the paper monitors burn, char, or become discolored after exposing the specimens to the ignition source, the material is classified as Class I.

Class I textiles are generally considered by the trade as having no unusual burning characteristics and acceptable for use in manufacturing blankets.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Photo Appendix

Sample as received

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.