

TEST REPORT

Test Report # 16H-09403(R1) Date of Report Issue: January 10, 2017
Date of Sample Received: January 3, 2017 Pages: Page 1 of 4

CLIENT INFORMATION:

Company: BIC Graphic
Recipient: 14421 Myerlake Circle
Clearwater
Florida
33760
United States (USA)



SAMPLE INFORMATION:

Description: Bity Buds
Assortment: - Purchase Order Number: 7986
Item No.: 32074_CAR Country of Origin: China
Country of Distribution: United States, Canada Labeled Age Grade: -
Quantity Submitted: 3 pcs per style Recommended Age Grade: -
Testing Period: 01/03/2017 – 01/05/2017 Tested Age Grade: -
Previous Test Report #: 16H-08257

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Loska Yeung Lok Ka
Leader, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST RESULTS SUMMARY:

At the request of the client, the following test was conducted:

| CONCLUSION | TEST(S) CONDUCTED |
|------------|--|
| PASS | California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP) |

Remark:

† Revised information and supersedes the previous Report no. 16H-09403.

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Test Method: CPSC-CH-C1001-09.3
 Analytical Method: Gas Chromatography with Mass Spectrometry

| Specimen No. | | 1 | 5 | --- | --- | Limit (ppm) |
|------------------------------------|--------------------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | CAS No. | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| Dibutyl phthalate (DBP) | 84-74-2 | ND | ND | --- | --- | 1000 |
| Benzyl butyl phthalate (BBP) | 85-68-7 | ND | ND | --- | --- | 1000 |
| Di-(2-ethylhexyl) phthalate (DEHP) | 117-81-7 | ND | ND | --- | --- | 1000 |
| Diisononyl phthalate (DINP) | 28553-12-0 68515-48-0 | 340 | ND | --- | --- | 1000 |
| Diisodecyl phthalate (DIDP) | 26761-40-0 68515-49-1 | ND | ND | --- | --- | 1000 |
| Di-n-hexyl phthalate (DnHP) | 84-75-3 | ND | ND | --- | --- | 1000 |
| Conclusion | | PASS | PASS | --- | --- | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)
 LT = Less than
 ND = Not detected (Reporting Limit = 100 ppm)
 Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location |
|--------------|----------------------|--|
| 1 | White soft PVC | White plastic USB casing (white style) |
| 5 | Dull white soft PVC | White plastic cord (white style) |

†SAMPLE PHOTO:



-End Report-