

No.SET2016-18773

TEST REPORT

Client Name The House of Marley, LLC

Name of product GET TOGETHER

Manufacturer The House of Marley, LLC

Model EM-JA006B

Test sort Commission Test



CCIC Southern Electronic Product Testing (Shenzhen) Co., Ltd.

Address: Electronic Testing Building, No. 43 Shahe Road, Xili Jiedao, Nanshan District, 518055 Shenzhen, Guangdong, China

P.C.: 518055

TEL: 86-755-26627338

FAX: 86-755-26627238

Internet: [http:// www.ccic-set.com](http://www.ccic-set.com)

E-Mail: manager@ccic-set.com



Customer information	Client	The House of Marley, LLC
	Address	3000 Pontiac Trail, Commerce Township, MI48390, USA
Sample information	Name of sample	GET TOGETHER
	Model	EM-JA006B
	Trade mark	MARLEY
	Manufacturer	The House of Marley, LLC
	Address	3000 Pontiac Trail, Commerce Township, MI48390, USA
Test information	Sample received	Oct. 25, 2016, Oct. 31, 2016
	Testing date	Oct. 25, 2016~ Nov. 07, 2016
	Test sort	Commission Test
	Requested/item	(1)US California Proposition 65. on Lead content (2)US California Proposition 65. on Phthalates content (DBP, BBP, DEHP, DIDP, DnHP, DINP, DNOP)
	Standard/Foundation	(1) With reference to CPSC-CH-E1001-08.3&CPSC-CH-E1002-08.3&CPSC-CH-E1003-09.1, and analysis was performed by ICP-OES. (2) With reference to CPSC-CH-C1001-09.3, and analysis was performed by GC-MS
	Conclusion	Please see the detecting data.
Remark	According to client's requirement, all test result of Sample No.8&12, No.9, No.10, No.38 quote from No.8, No.7, No.19, No.18 report No. SET2016-11100.	

Tested By:

Liu Yaru

Checked By:

Calvin

Approved By:

Billow

Date:

Nov. 11, 2016

Date:

Nov. 11, 2016

Date:

Nov. 11, 2016



Tested components:

No.	COMPONENTS	COLOR AND MATERIAL	TEST ITEM
1	GET TOGETHER	Black plastic film (small horn)	Lead, Phthalates
2		Black plastic support (small horn)	
3		Transparent varnish (main body)	
4		Brown bamboo (main body)	
5		Black soft plastic kin (horn edgefold)	
6		Black plastic skin	
7		Cloth with backside plastic skin (main body)	
8		White ink (key)	
9		Transparent plastic lamp	
10		Transparent soft plastic (key)	
11		Black soft plastic (foot mat)	
12		White ink (label)	
13		USB white plastic plug core	
14		Black plastic jack outer shell	
15	Silvery metal USB outer shell	Lead	
16	Black plastic	Lead, Phthalates	
17	Translucence white plastic lamp		
18	Black plastic jack		
19	Black plastic (adaptor outer shell)		
20	Label (adaptor)		
21	Wire jacket (adaptor)		
22	Black soft plastic (adaptor SR)		
23	Black soft plastic plug outer shell (adaptor)		
24	Black plastic mixed test (all conversion head base seat)		
25	Black plastic mixed test (all conversion head encapsulation)		







No.	COMPONENTS	COLOR AND MATERIAL	TEST ITEM
26	GET TOGETHER	Varnish on light color wood	Lead, Phthalates
27		Light color wood	
28		Metal pin (conversion head)	Lead
29		Metal pin (conversion head)	
30		Metal contact sheet (adaptor)	
31		Metal plug (adaptor)	
32		Metal plug core (adaptor)	
33		Black plastic plug core (adaptor)	Lead, Phthalates
34		Light gray ink	
35		Black plastic (backside board)	
36		Loudspeaker box outer blue cloth	
37		Loudspeaker box black cloth	
38		Label black coating	

Sample photo:





Detailed Split Chart:





Detailed Split Chart:





Test result:

(1)US California Proposition 65. on Lead content

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		1	2	3	4	5		6
Lead		N.D.	68	27	N.D.	N.D.	N.D.	2

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		7	8	9	10	11		12
Lead		N.D.	15	N.D.	N.D.	N.D.	15	2

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		13	14	15	16	17		18
Lead		N.D.	N.D.	50	N.D.	N.D.	N.D.	2

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		19	20	21	22	23		#24
Lead		N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	2

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		#25	26	27	28	29		30
Lead		N.D.	N.D.	N.D.	60	58	N.D.	2

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)	
		31	32	33	34	35		36
Lead		N.D.	43	N.D.	N.D.	N.D.	N.D.	2



Item	Sample No.	Concentration (mg/kg)		MDL (mg/kg)
		37	38	
Lead		N.D.	N.D.	2

Note:-

MDL= Method Detection Limit,

#= According to the applicant's request, the admixture of specimen is tested, the testing results of specimen may be different from that of any sole material in specimen.

(2)US California Proposition 65. on Phthalates content

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
		1	2	3	4	5	
Dibutyl phthalate (DBP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Benzylbutyl phthalate (BBP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Di-2-ethylhexyl phthalate (DEHP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Diisodecyl phthalate (DIDP)		N.D.	N.D.	N.D.	N.D.	N.D.	50
Di-n-hexyl phthalate (DnHP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Diisononyl phthalate (DINP)		N.D.	N.D.	N.D.	N.D.	N.D.	50
Di-n-octyl phthalate (DNOP)		N.D.	N.D.	N.D.	N.D.	N.D.	30

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
		6	7	8	9	10	
Dibutyl phthalate (DBP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Benzylbutyl phthalate (BBP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Di-2-ethylhexyl phthalate (DEHP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Diisodecyl phthalate (DIDP)		N.D.	N.D.	N.D.	N.D.	N.D.	50
Di-n-hexyl phthalate (DnHP)		N.D.	N.D.	N.D.	N.D.	N.D.	30
Diisononyl phthalate (DINP)		N.D.	N.D.	N.D.	N.D.	N.D.	50
Di-n-octyl phthalate (DNOP)		N.D.	N.D.	N.D.	N.D.	N.D.	30



Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
	11	12	13	14	16		
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisodecyl phthalate (DIDP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-hexyl phthalate (DnHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisononyl phthalate (DINP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-octyl phthalate (DNOP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
	17	18	19	20	21		
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisodecyl phthalate (DIDP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-hexyl phthalate (DnHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisononyl phthalate (DINP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-octyl phthalate (DNOP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	



Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
	22	23	#24	#25	26		
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisodecyl phthalate (DIDP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-hexyl phthalate (DnHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisononyl phthalate (DINP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-octyl phthalate (DNOP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	

Item	Sample No.	Concentration (mg/kg)					MDL (mg/kg)
	27	33	34	35	36		
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisodecyl phthalate (DIDP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-hexyl phthalate (DnHP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	
Diisononyl phthalate (DINP)	N.D.	N.D.	N.D.	N.D.	N.D.	50	
Di-n-octyl phthalate (DNOP)	N.D.	N.D.	N.D.	N.D.	N.D.	30	




Item	Sample No.	Concentration (mg/kg)		MDL (mg/kg)
	37	38		
Dibutyl phthalate (DBP)	N.D.	N.D.	30	
Benzylbutyl phthalate (BBP)	N.D.	N.D.	30	
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	30	
Diisodecyl phthalate (DIDP)	N.D.	N.D.	50	
Di-n-hexyl phthalate (DnHP)	N.D.	N.D.	30	
Diisononyl phthalate (DINP)	N.D.	N.D.	50	
Di-n-octyl phthalate (DNOP)	N.D.	N.D.	30	

Note:- MDL= Method Detection Limit

[#]= According to the applicant's request, the admixture of specimen is tested, the testing results of specimen may be different from that of any sole material in specimen.


Test Process:

Pb





Phthalates



List of apparatus:

No.	Name	Model	Calibration Valid Date	USE(√)
1	ICP-OES	VISTA-MPX	2017/07/24	√
2	GC-MS	5975i	2017/07/24	√

***** END OF REPORT *****

STATEMENT

1. The test report is invalid without stamp of laboratory.
2. The test report is invalid without signature of person(s) testing and authorizing.
3. The test report is invalid if erased and corrected.
4. Test results of the report is valid to the test samples if sampling by client.
5. “☆” item to be outside the scope of authorized by CNAS.
6. The test report shall not be reproduced except in full, without written approval of the laboratory.
7. If there is any objection to report, the client should inform issuing laboratory within 15 days from the date of receiving test report.