



TEST REPORT

Test Report # 18H-007959(A2) Date of Report Issue: November 6, 2018
Date of Sample Received: October 15, 2018 Pages: Page 1 of 6

CLIENT INFORMATION:

Company: BIC Graphic
Recipient: 14421 Myerlake Circle
Clearwater
Florida
33760
United States (USA)



SAMPLE INFORMATION:

Description: mybevi™ 26 oz Brute Tumbler & mybevi™ 26 oz Classic Tumbler
Assortment: - Test Request Form No.: 2372
Item No.: 46260 & 46261 Country of Origin: United States
Shipment Order No.: - Labeled Age Grade: -
Country of Distribution: United States, Canada Recommended Age Grade: -
Quantity Submitted: Refer to Page 2 Tested Age Grade: -
Testing Period: 10/16/2018 – 10/24/2018

OVERALL RESULT:

FAIL

Refer to page 3 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



QUANTITY SUBMITTED DETAILED:

Style description	Qty.
mybevi 26oz Brute Tumbler - Blue	1 pc
mybevi 26oz Brute Tumbler - Black	1 pc
mybevi 26oz Brute Tumbler - Grey	2 pcs
mybevi 26oz Classic Tumbler - Blue	1 pc
mybevi 26oz Classic Tumbler - Black	1 pc
mybevi 26oz Classic Tumbler - Silver	2 pcs



TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
FAIL	FDA 21 CFR 177.1520, Polypropylene Homopolymers

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Homopolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			2	3	RL	Limit
Test Item	Temp.	Duration	Result	Result		
n-Hexane extractive (%)	Reflux	2 hours	11.3	4.0	0.1	6.4
Xylene extractive (%)	120°C	2 hours or until total dissolved	22.5	10.8	0.5	9.8
Conclusion			FAIL	FAIL		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 1.1.


By client's request, density and melting point were not conducted in FDA 21 CFR 177.1520 PP-homo.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
2	Black plastic (PP-homo)	Black polypropylene slider (46260 & 46261) (all black styles)
3	Blue plastic (PP-homo)	Blue polypropylene slider (46260 & 46261) (all blue styles)



FAILURE PHOTO:



C01



SAMPLE PHOTO:



-End Report-